

PipeMark 810

AWS A5.5 E8010-P1
AWS A5.5M E5510-P1
EN ISO 2560-A E 46 4 1Ni C 25
EN ISO 2560-B E 55 10-P1 A

Characteristics and Applications:

PipeMark 810 is a cellulose electrode for both vertical-down welding of high strength large diameter pipelines. It is excellent for root passes, hot passes, filler and cover layers, especially recommended for root pass welding. PipeMark 810 is designed for DCEP and DCEN welding. The welding in vertical down and all position can be done with stable arc, good slag detachability, and deep penetration. It is suitable for the welding of pressure pipes, oil tanks, and boilers.

Notes on usage:

1. Be sure to clean up the contaminations on the base metal.
2. Not allow to re-dry electrode


Typical chemical composition of weld metal (wt%):

C	Mn	Si	P	S
0.13	1.0	0.10	0.015	0.01

Typical mechanical properties of weld metal:

Yield strength MPa(ksi)	Tensile strength MPa(ksi)	Elongation %	Charpy V-Notch J (ft-lbf) -30°C (-20°F)
550(80)	650(94)	22	41(30)

Welding position:



Sizes and recommended current range (DC $\langle \pm \rangle$):

Diameter (mm)	2.4	2.6	3.2	4.0	4.8
Length (mm)	350		350	350	350
Amps	50-70		60-100	90-140	140-200

Base Materials:

EN: L415NB-L485NB, L415MB-L485MB

API 5 L: X56, X60, X65, X70

* The information contained or otherwise referenced herein is presented only as "typical" without guarantee or warranty, and TienTai Electrode Co., Ltd. expressly disclaims any liability incurred from any reliance thereon. Typical data is obtained when welded and tested in accordance with AWS specification. Other tests and procedures may produce different results. No data is to be construed as recommendation for any welding condition or technique not controlled by TienTai Electrode Co., Ltd.