

TAC-16

AWS A5.5 E7018-W1
JIS Z 3214 DA5016G

Characteristics and Applications:

TAC-16 is for the welding of 490N/mm² grade high tensile weathering steel. The welding can be done in all positions with good atmospheric corrosion resistance, good X-ray soundness, and good crack resistance. The weld metal contains Cu and Ni. It is suitable for 490N/mm² high tensile steel (ASTM A588, COR-TEN A, B), and also for SPA-H, SMA 490 steel.

Notes on usage:

1. Dry the electrodes at 350-400°C for 60 minutes before using.
2. Do not exceed the range of recommended current. Over heat input might decrease the impact value.
3. Maintain short arc length. Moving range should be controlled within 3 times of the wire's dia when you are welding with weave method.
4. While applying in plate with high restraint (such as the plate is thicker than 25mm), pre-heating at 80~100°C is recommended.
5. Be sure to clean up the contaminations on the base metal and welding seam so as not to derogate the weld metal quality from particles.
6. Use back-step method to prevent arc starting from blowholes and hold for 3-5 seconds at every end-up.

Typical chemical composition of weld metal (wt%):

C	Mn	Si	P	S	Cu	Ni	Cr
0.06	0.60	0.50	0.018	0.010	0.5	0.35	0.25

Typical mechanical properties of weld metal:

Yield strength MPa(ksi)	Tensile strength MPa(ksi)	Elongation %	Charpy V-Notch J (ft-lbf) -20°C (0°F)
515(75)	610(88)	30	140(103)

Welding position:



Sizes and recommended current range (AC or DC <+>):

Diameter (mm)	3.2	4.0	5.0
Length (mm)	350	450	450
Amps	F	100-140	140-180
	V&OH	90-110	130-160

* The information contained or otherwise referenced herein is presented only as "typical" without guarantee or warranty, and TienTai Electrode Co., Ltd. expressly disclaims any liability incurred from any reliance thereon. Typical data is obtained when welded and tested in accordance with AWS specification. Other tests and procedures may produce different results. No data is to be construed as recommendation for any welding condition or technique not controlled by TienTai Electrode Co., Ltd.