

FabStar 82G

AWS A5.26 EG82T-G

Characteristics and Applications:

FabStar 82G is a self-shielded flux-cored wire used for single pass, vertical up, electrogas welding (EGW) of storage tank, shipbuilding, heavy equipment fabrication and structural welding. It provides good low-temperature impact toughness at -46°C. It is suitable for welding 590N/mm² high tensile steels with high deposition rate and without consumable guide.

Notes on Usage:

1. Use DC(+) polarity.
2. Mechanical properties are dependent on plate chemistry and joint geometry.
3. Pre-heat the workpiece and star-up zone.
4. Baffle plate should be tightened firmly to prevent a leak of deposited metal.
5. Control all parameters with cares during welding, such as shape of weld joint, cooling rate.
6. Keep the product dry, while it is stored or delivered.

Typical chemical composition of weld metal (wt%)

C	Mn	Si	P	S	Ni	Mo
0.04	1.37	0.34	0.013	0.008	1.3	0.14

Typical mechanical properties of weld metal on A36 base metal

Yield strength MPa(ksi)	Tensile strength MPa(ksi)	Elongation %	Charpy V-Notch J (ft-lbf) -46°C(-50°F)
530(77)	625(91)	26	50(37)

Sizes and recommended current range (DC < + >)

Diameter (mm)	
Parameters	φ1.6
Plate thickness (mm)	9-16
Current (Amps)	250-300
Voltage(Volt)	28-32

* The information contained or otherwise referenced herein is presented only as "typical" without guarantee or warranty, and TienTai Electrode Co., Ltd. expressly disclaims any liability incurred from any reliance thereon. Typical data is obtained when welded and tested in accordance with AWS specification. Other tests and procedures may produce different results. No data is to be construed as recommendation for any welding condition or technique not controlled by TienTai Electrode Co., Ltd.