

TFW-309LTM

AWS A5.22 E309LT0-4
EN ISO 17633-A-T 23 12 L R M21 3
JIS Z 3323 TS 309L-F M2 1 0

Characteristics and Applications:

TFW-309LTM is designed for flat position welding by gas shield of mix gas (75~80% Argon and 25~20% CO₂). It is commonly used for welding similar alloys in wrought or cast forms, also used in welding dissimilar metals, such as joining Type 304 to mild steel.

Notes on usage:

1. Before welding, oil, rusty, and moisture should be cleaned off the base material that should have the proper protection from the wind in welding site.
2. Use with mix gas (75~80% Argon and 25~20% CO₂).
3. Keep the product dry, while it is stored or delivered.

Typical chemical composition of weld metal (wt%):

C	Mn	Si	P	S	Cr	Ni
0.022	1.63	0.66	0.022	0.008	23.65	12.85

Typical mechanical properties of weld metal:

Tensile strength MPa(ksi)	Elongation %
550(80)	36

Welding position:



Sizes and recommended parameter range (DC < + >):

Stick out:15-20(mm),flow rate:20-25(l/min):

Diameter (mm)	1.2
Position	
F, HF	130A-220A/24V-33V

* The information contained or otherwise referenced herein is presented only as "typical" without guarantee or warranty, and TienTai Electrode Co., Ltd. expressly disclaims any liability incurred from any reliance thereon. Typical data is obtained when welded and tested in accordance with AWS specification. Other tests and procedures may produce different results. No data is to be construed as recommendation for any welding condition or technique not controlled by TienTai Electrode Co., Ltd.