

TFW-316LP

AWS A5.22 E316LT1-4
EN ISO 17633-A T 19 12 3 L P M21 1

Characteristics and Applications:

TFW-316LP is designed for all position welding by gas shield of mix gas (75~80% Argon and 25~20% CO₂). An austenitic stainless steel deposit can be used for joining Types 316,316L,CF-8M, and CF-3M stainless steels. The product provides high resistance to inter-granular corrosion with low carbon weld deposit.

Notes on usage:

- 1.Before welding, the base metal should be cleaned from oil, rusty, moisture and it should have the proper protection from the wind in welding site.
- 2.Use with mix gas (75~80% Argon and 25~20% CO₂).


Typical chemical composition of weld metal (wt%):

C	Mn	Si	P	S	Cr	Ni	Mo
0.026	1.35	0.49	0.023	0.010	18.95	12.52	2.70

Typical mechanical properties of weld metal:

Tensile strength MPa(ksi)	Elongation %
629(91)	38

Welding position:



Size and recommended parameter range (DC<+>)

Stick out:15-20(mm),flow rate:20-25(l/min):

Position	Diameter (mm)	1.2
F, HF		130A-220A/24V-33V
H		140A-180A/25V-29V
V-UP		130A-180A/24V-28V
V-down		150A-180A/25V-29V
OH		150A-180A/25V-29V

* The information contained or otherwise referenced herein is presented only as "typical" without guarantee or warranty, and TienTai Electrode Co., Ltd. expressly disclaims any liability incurred from any reliance thereon. Typical data is obtained when welded and tested in accordance with AWS specification. Other tests and procedures may produce different results. No data is to be construed as recommendation for any welding condition or technique not controlled by TienTai Electrode Co., Ltd.