

TWE-707-O

AWS A5.20 E70T-7
EN ISO 17632-A-T 42 Z W N 3

Characteristics and Applications:

TWE-707-O is a self-shielded flux cored wire designed for high penetration welding. It is suitable for flat, horizontal and downhill positions on DCEN polarity. Excellent performance on X-ray inspection, and desulfuration reduces cracking in welding thick plates, constrained joints and medium-carbon steel. The typical applications of TWE-707-O are general fabrication and structural weldment where high deposition with good penetration and / or fast travel speed is needed. Available positions are flat weld, horizontal weld and vertical down ones of welding for fillet weld and lap joint.

Notes on usage:

1. DC(-) polarity is recommended.
2. TM-70C or TWE-711 are recommended when impact toughness of weld metal is essential.
3. Keep the product dry, while it is stored or delivered.

Typical chemical composition of weld metal (wt%):

C	Mn	Si	P	S	Al
0.29	0.45	0.10	0.010	0.005	1.45

Typical mechanical properties of weld metal:

Yield strength MPa(ksi)	Tensile strength MPa(ksi)	Elongation %
453(66)	600(87)	25

Welding position:



Sizes and recommended parameter range (DC <->):

Stick out: 40-60 (mm)

Position	Diameter (mm)			
	1.6	2.0	2.4	2.8
F, HF	240A-280A/ 24V-28V	250A-350A/ 24V-32V	250A-400A/ 26V-34V	280A-450A/ 28V-36V

* The information contained or otherwise referenced herein is presented only as "typical" without guarantee or warranty, and TienTai Electrode Co., Ltd. expressly disclaims any liability incurred from any reliance thereon. Typical data is obtained when welded and tested in accordance with AWS specification. Other tests and procedures may produce different results. No data is to be construed as recommendation for any welding condition or technique not controlled by TienTai Electrode Co., Ltd.