TWE-715M

AWS A5.20 E71T-5M EN ISO 17632-A-T 46 3 P M 1 H10

Characteristics and Applications:

TWE-715M is an all-position flux-cored wire designed to be used with Ar/ CO₂ gas mixture for 490N/mm² grade high tensile steel. Its low temperature impact toughness is better than E71T-1M(AWS A5.20). The typical applications of TWE-715M are constructional steel, machinery and shipbuilding.

Notes on usage:

- 1. DC(+) polarity is recommended.
- 2. Use 75~80%Ar+25~20%CO2 as shielding gas.
- 3. Keep inter-pass temperature under you aer 150°C whre in multiple-pass welding.
- 4. Keep the product dry, while it is stored or delivered.


Typical chemical composition of weld metal (wt%):

С	Mn	Si	Р	S
0.04	1.35	0.30	0.013	0.007

Typical mechanical properties of weld metal:

Yield strength MPa(ksi)	Tensile strength MPa(ksi)	Elongation %	Charpy V-Notch J (ft-lbf) -30°C (-20°F)
564(82)	607(88)	26	75(55)

Welding position:



Sizes and recommended current range (DC<+>): Stick out:15-25(mm), gas flow rate:20-25(I/min):

Diameter (mm) Parameters	1.2
F, HF, VU,OH, VD, H	140A-300A/22V-33V

^{*}The information contained or otherwise referenced herein is presented only as "typical" without guarantee or warranty, and TienTai Electrode Co., Ltd. expressly disclaims any liability incurred from any reliance thereon. Typical data is obtained when welded and tested in accordance with AWS specification. Other tests and procedures may produce different results. No data is to be construed as recommendation for any welding condition or technique not controlled by TienTai Electrode Co., Ltd.

