

TWH-17-S

/TF-81

Characteristics and Applications:

TWH-17-S/TF-81 is a submerged arc flux-cored wire / flux which produces a low carbon, low alloy weld deposit with a typical hardness of HRC 37. It features good resistance to compression and cold work deformation. The impact resistance is excellent and the crack susceptibility is low. After welding, the deposit could be flame cut or machined. TWH-17-S can be used for both build-up and hardfacing on rollers and idlers where there is metal-to-metal wear. Typical applications include carbon steel crane wheels, idlers, mine car wheels and house rollers, etc..

Notes on usage:

- 1.TWH-17-S has good resistance to cross checking and is not restricted with regard to deposit thickness.
- 2.Applications that are inherently crack sensitive may require one or more of the following:
 - High preheat and interpass temperatures at 204-260°C.
 - Controlled slow cooling.
 - Stress relieving at 480°C.
 - Minimize layer thickness.

Typical chemical composition (wt%):

C	Mn	Si	Cr	Mo
0.07	2.6	0.6	2.7	0.7

Range of weld metal hardness (on mild steel):

Layer	1st layer	2nd layer	3rd layer
Hardness (HRC)	26-30	30-35	34-37

Suggested welding parameter DC(<+>):

Diameter (mm)	3.2
Parameters	
Volt	25-32
Amps	300-450
Stick out(mm)	30-40

* The information contained or otherwise referenced herein is presented only as "typical" without guarantee or warranty, and TienTai Electrode Co., Ltd. expressly disclaims any liability incurred from any reliance thereon. Typical data is obtained when welded and tested in accordance with AWS specification. Other tests and procedures may produce different results. No data is to be construed as recommendation for any welding condition or technique not controlled by TienTai Electrode Co., Ltd.