

TWE-811Ni1

AWS A5.29 E81T1-Ni1C
EN ISO 17632-A-T 46 3 1Ni P C1 1 H10

Characteristics and Applications:

TWE-811Ni1 is a titania type flux-cored wire with CO₂ shielding gas for all-position welding. It is designed for welding 590 N/mm² high tensile steel used in low temperatures.

It provides good weldability with smooth bead appearance, less spatter and stable arc as well as good impact properties down to -30°C.

It is also suitable for welding on construction machinery, shipbuilding, offshore, structures, bridges, storage tanks and piping.

Notes on usage:

1. Excessive heat input should reduce impact value. Therefore, perform welding with selecting proper heat input based on the required impact value.
2. Must preheat at 50~150°C depending on steels, plate thickness and restraint.
3. Use DC(+) polarity.
4. Use 99.8% or higher purity of CO₂ Gas.
5. Keep the product dry, while it is stored or delivered.


Typical chemical composition of weld metal (wt%):

C	Mn	Si	P	S	Ni
0.04	1.20	0.25	0.015	0.009	1.00

Typical mechanical properties of weld metal:

Yield strength MPa(ksi)	Tensile strength MPa(ksi)	Elongation %	Charpy V-Notch J(ft-lbf)		PWHT
			-30°C(-20°F)	110(81)	
602(87)	650(94)	26	-40°C(-40°F)	95(70)	--
			-40°C(-40°F)	92(68)	590°C*8hr
522(76)	590(86)	30	-40°C(-40°F)	92(68)	590°C*8hr

Welding position:



Sizes and recommended parameter range (DC<+>) :

Stick out:15-25(mm), flow rate:20-25(l/min):

Diameter (mm)	1.2	1.4	1.6
Position			
F、HF	180A-300A / 24V-36V	180A-350A / 24V-36V	200A-400A / 28V-42V
VU、OH	150A-220A / 22V-28V	150A-220A / 22V-28V	160A-280A / 22V-28V
H	150A-260A / 22V-31V	160A-280A / 22V-30V	180A-400A / 28V-42V

* The information contained or otherwise referenced herein is presented only as "typical" without guarantee or warranty, and TienTai Electrode Co., Ltd. expressly disclaims any liability incurred from any reliance thereon. Typical data is obtained when welded and tested in accordance with AWS specification. Other tests and procedures may produce different results. No data is to be construed as recommendation for any welding condition or technique not controlled by TienTai Electrode Co., Ltd.