

# TM-70C

AWS A5.20 E70T-1C  
EN ISO 17632-A-T 46 2 R C1 3 H10  
JIS Z 3313 T49J0T15-0C A-U

## Characteristics and Applications:

TM-70C is a high deposition rate flux cored wire suitable for high speed fillet welding application in flat and horizontal position. The wire has excellent porosity resistibility for use in welding over zinc-primer surface and mill scale in high speed fillet welding. The wire generates low spatter and produces thinner slag with good slag detachability. In addition it produces deep effective throat on fillet weld and it has good arc stability and welder appeal.

TM-70C is widely used in shipbuilding, bridge construction and structural fabrication.

## Notes on usage:

1. Must properly pre-heating 50~150°C(120~300°F) and use inter-pass temperature in order to release hydrogen which may cause cracking in weld metal when you weld on medium and heavy plates.
2. Use DC(+) polarity and 100% CO<sub>2</sub> shielding gas.
3. Maintain the temperature of inter-pass under 150°C with multiple-pass welding.
4. Keep the product dry while it is stored or delivered.

## Typical chemical composition of weld metal (wt%):

C	Mn	Si	P	S
0.05	1.40	0.45	0.011	0.008

## Typical mechanical properties of weld metal:

Yield strength MPa(ksi)	Tensile strength MPa(ksi)	Elongation %	Charpy V-Notch J(ft-lbf)	
			-20°C (0°F)	-30°C (-20°F)
540(78)	590(86)	28	80(59)	60(44)

## Welding position:



## Sizes and recommended parameter range ( DC < + > ):

Stick out: 15-25 (mm), flow rate: 20-25 (l/min)

Diameter (mm)	1.2	1.4	1.6
Position			
F、H、HF	160A-300A / 24V-36V	200A-350A / 26V~34V	270A-400A / 28V-40V

\* The information contained or otherwise referenced herein is presented only as "typical" without guarantee or warranty, and TienTai Electrode Co., Ltd. expressly disclaims any liability incurred from any reliance thereon. Typical data is obtained when welded and tested in accordance with AWS specification. Other tests and procedures may produce different results. No data is to be construed as recommendation for any welding condition or technique not controlled by TienTai Electrode Co., Ltd.