

TM-70

AWS A5.18 E70C-3M/6M
EN ISO 17632-A-T 42 2 M M21 3 H5
JIS Z 3313 T 49 0 T15-0 MA

Characteristics and Applications:

TM-70 is a metallic flux cored wire designed to be used with Ar/CO₂ for mild steel and 490N/mm² high tensile steel, its deposition rate is 10-30% higher than a solid wire.

Multi-layer welding can be performed without removing slag. Smooth arc characteristics low diffusible hydrogen weld deposit low smoke and spatter levels. It is suitable for steel structure, bridges, shipbuilding, vehicles, storage tanks, etc.

Notes on usage:

1. Use DC(+) polarity.
2. When you use larger diameters (1.6mm or higher), we recommend higher power supply of welder.
3. Trailer Shield is essential to ensure that the weld pool is completely shielded by 75~80%Ar-25~20% CO₂ gas until solidification is complete and no porosity problem.
4. Inter-pass temperature should be under 150°C while in multiple-pass welding.
5. Keep the product dry, while it is stored or delivered.

Typical chemical composition of weld metal (wt%):

C	Mn	Si	P	S
0.05	1.45	0.47	0.012	0.008

Typical mechanical properties of weld metal:

Yield strength MPa(ksi)	Tensile strength MPa(ksi)	Elongation %	Charpy V-Notch J(ft-lbf)	
			-20°C (0°F)	-30°C (-20°F)
488(71)	559(81)	31	70(52)	58(43)

Welding position:



Sizes and recommended current range (DC<+>):

Stick out: 15-25 (mm), flow rate: 20-25 (l/min)

Parameters	Diameter (mm)	1.2	1.6
	F, HF		240A-320A/26V-34V

* The information contained or otherwise referenced herein is presented only as "typical" without guarantee or warranty, and TienTai Electrode Co., Ltd. expressly disclaims any liability incurred from any reliance thereon. Typical data is obtained when welded and tested in accordance with AWS specification. Other tests and procedures may produce different results. No data is to be construed as recommendation for any welding condition or technique not controlled by TienTai Electrode Co., Ltd.