# PipeMark 710

AWS A5.5 E7010-P1 EN ISO 2560-B E4910-P1 A

### **Characteristics and Applications:**

PipeMark 710 is a cellulose electrode for both vertical-down welding of high strength large diameter pipelines. The product is excellent for root passes, hot passes, filler and cover layers. Especially recommended for root pass welding. PipeMark 710 is designed for DCEP and DCEN welding. The product can be applied to vertical-down and all position welding and features with stable arc, good slag detachability, and deep penetration. It is suitable for the welding of pressure pipes, oil tanks, and boilers.

#### Notes on usage:

- 1. Be sure to clean up the contaminations on the base metal.
- 2. Not allow to re-dry electrode

#### Typical chemical composition of weld metal (wt%):

	С	Mn	Si	Р	S
AWS	≦0.20	≦1.20	≦0.60	≦0.03	≦0.03
EN ISO	≦0.20	≦1.20	≦0.60	≦0.03	0.03
Typical value	0.12	0.8	0.12	0.015	0.010

#### Typical mechanical properties of weld metal:

	Yield strength MPa(ksi)	Tensile strength MPa(ksi)	Elongation %	Charpy V-Notch J (ft-lbf) -30°C (-20°F)
AWS	<b>≥410(60)</b>	≥490(70)	≥22	≥27(20)
EN ISO	≥420(61)	≥490(70)	≥20	≥27(20)
Typical value	520(75)	630(91)	22	40(30)

## Welding position:











## Sizes and recommended current range ( $DC < \pm >$ ):

Diameter (mm)	2.4	2.6	3.2	4.0	4.8
Length (mm)	350		350	350	350
Amps	50-70		60-100	90-140	140-200

#### **Base Materials:**

**EN:** S235JR, S275JR, S235J2G3, S275J2G3, S355J2G3, P235GH, P265GH, P355T1, P235T2-P355T2, L210-L415NB, P235G1TH, P255G1TH. Root pass up to L480MB

**API 5 L:** A, B, X 42, X 46, X 52, X56, X60. Root pass up to X 70.

<sup>\*</sup> The information contained or otherwise referenced herein is presented only as "typical" without guarantee or warranty, and TienTai Electrode Co., Ltd. expressly disclaims any liability incurred from any reliance thereon. Typical data is obtained when welded and tested in accordance with AWS specification. Other tests and procedures may produce different results. No data is to be construed as recommendation for any welding condition or technique not controlled by TienTai Electrode Co., Ltd.

