

TF-210

Basicity index: 3.1

EN ISO 14174 S A FB 1 55 AC H5

Characteristics and Applications:

TF-210 is a fluoride-basic flux with high basicity and low impurity levels such as P and S. It is suitable for welding on DC and AC using single and tandem wire process.

It also specially suited to narrow gap welding on AC. It provides excellent weld-ability and due to neutral behavior, high mechanical properties of weld metal can be controlled by using the appropriate wire grade.

- Fine grain structural steels for low temperature requirements.
- Offshore applications.
- High tensile fine grain steels.

Notes on usage:

1. Flux exposed to atmosphere for an excess period must be re-baked at 300~350°C for 2~4hr holding time.
2. Re-circulation of flux should be limited to three cycles. After this, the flux should be mixed with twice its volume of new flux prior to further use.
3. We recommend using heated hoppers for storage of flux in production.

Typical chemical composition of weld metal (wt %) :

Wire	EN ISO 14171-A	C	Mn	Si	P	S
TSW-12KH	S 42 6 FB S3Si	0.08	1.50	0.39	0.014	0.005
TSW-12KM	S 38 5 FB S2Si	0.06	1.16	0.32	0.015	0.005

Typical mechanical properties of weld metal:

Wire	AWS A5.17	Yield strength MPa(ksi)	Tensile strength MPa(ksi)	Elongation %	Charpy V-Notch J (ft-lbf)	Temperature °C(°F)
TSW-12KH	F7A8-EH12K	430(62)	520(75)	32	145(107)	-51(-60)
					120(89)	-62(-80)
TSW-12KM	F7A6-EM12K	414(60)	493(72)	34	190(140)	-51(-60)

* The information contained or otherwise referenced herein is presented only as "typical" without guarantee or warranty, and TienTai Electrode Co., Ltd. expressly disclaims any liability incurred from any reliance thereon. Typical data is obtained when welded and tested in accordance with AWS specification. Other tests and procedures may produce different results. No data is to be construed as recommendation for any welding condition or technique not controlled by TienTai Electrode Co., Ltd.