

TC-70A1

AWS A5.5 E7010-A1
EN ISO 2560-B-E4910-1M
JIS Z 3223 E4910-1M3

Characteristics and Applications:

TC-70A1 is a high cellulose type electrode for DC(+) welding. The welding can work in all positions with good crack resistance, deep penetration, stable arc, and excellent weldability when the welding condition is difficult due to narrow space or other reasons. It is especially designed for welding of the pipes, high pressure pipes, oil tanks, and boilers due to its good X-ray soundness.

Notes on usage:

1. Dry the electrodes at 60-70°C for 30 minutes before using.
2. Lower current is recommended. Better to use straight or small weaving method for vertical-down position.
3. Pre-heat the workpiece at 100~200°C and PWHT at 620~680°C.
4. Use DC(+) polarity.

Typical chemical composition of weld metal (wt%):

	C	Mn	Si	P	S	Mo
AWS	≤0.12	≤0.60	≤0.40	≤0.03	≤0.03	0.40-0.65
Typical value	0.085	0.35	0.14	0.010	0.007	0.50

Typical mechanical properties of weld metal:

	Yield strength MPa(ksi)	Tensile strength MPa(ksi)	Elongation %	PWHT
AWS	≥390(57)	≥490(70)	≥22	620°Cx1hr
Typical value	510(74)	610(88)	30	620°Cx1hr

Welding position:



Sizes and recommended current range (DC<+>):

Diameter (mm)		2.6	3.2	4.0	4.8
Length (mm)		350	350	350	350
Amps	F	60-80	80-120	120-160	150-200
	V&OH	50-70	80-110	90-150	120-180

* The information contained or otherwise referenced herein is presented only as "typical" without guarantee or warranty, and TienTai Electrode Co., Ltd. expressly disclaims any liability incurred from any reliance thereon. Typical data is obtained when welded and tested in accordance with AWS specification. Other tests and procedures may produce different results. No data is to be construed as recommendation for any welding condition or technique not controlled by TienTai Electrode Co., Ltd.