

TWE-811Ni2

AWS A5.29 E81T1-Ni2C
EN ISO 17632-A-T 46 4 2Ni P C1 1 H10

Characteristics and Applications:

TWE-811Ni2 is a titania type flux-cored wire for all-position MAG welding. It provides good weldability with smooth bead appearance, less spatter and stable arc as well as good impact properties down to -40°C.

It is suitable for welding of 590 N/mm² high tensile strength steel on construction machinery, structures, bridges, storage tanks and piping.

Notes on usage:

1. Must pre-heating at 50~150°C varied on steels, plate thickness and restraint.
2. Mechanical properties might fall when heat input is over 35J/cm. Therefore, perform welding with lower welding current and heat input.
3. Maintain inter-pass temperature under 150°C in multi-pass welding to keep excellent mechanical properties.
Use 99.8% or higher purity of CO₂ Gas.
4. Use DC(+) polarity.
5. Keep dry during storage and delivery.


Typical chemical composition of weld metal (wt%) :

	C	Mn	Si	P	S	Ni
AWS	≤0.12	≤1.50	≤0.80	≤0.030	≤0.030	1.75-2.75
EN ISO	-	≤1.4	-	-	-	1.8-2.6
Typical value	0.04	1.10	0.35	0.012	0.008	2.45

Typical mechanical properties of weld metal:

	Yield strength MPa(ksi)	Tensile strength MPa(ksi)	Elongation %	Charpy V-Notch J (ft-lbf) -40°C (-40°F)
AWS	≥470(68)	550-690(80-100)	≥19	≥27(20)
EN ISO	≥460(67)	530-680(77-99)	≥20	≥47(35)
Typical value	540(78)	630(91)	26	85(63)

Welding position:



Sizes and recommended parameter range (DC <+>):

Stick out:15-25(mm), flow rate:20-25(l/min):

Position	Diameter(mm)	1.2	1.6
	F、HF		180-300A / 26V-36V
VU、OH		150-220A / 24V-28V	160-220A / 24V-28V

* The information contained or otherwise referenced herein is presented only as "typical" without guarantee or warranty, and TienTai Electrode Co., Ltd. expressly disclaims any liability incurred from any reliance thereon. Typical data is obtained when welded and tested in accordance with AWS specification. Other tests and procedures may produce different results. No data is to be construed as recommendation for any welding condition or technique not controlled by TienTai Electrode Co., Ltd.