

TWE-704-O

AWS A5.20 E70T-4
EN ISO 17632-A-T 46 Z W N 3

Characteristics and Applications:

TWE-704-O is a self-shielded flux-cored wire, it is designed for on site general fabrication and structural work requiring, good slag release and friendly to manage variant weld joints by longer sticking out. The welding for heavy machinery, large construction components is appropriate, also stiffens in large building. It is suitable for flat, horizontal and downhill positions, also it can be applied to build up the worn parts.

Notes on usage:

1. DC(+) polarity is recommended.
2. TM-70C or TWE-711 are recommended when impact toughness of weld metal is essential.
3. Keep the product dry, while it is stored or delivered.


Typical chemical composition of weld metal (wt%):

| | C | Mn | Si | P | S | Al |
|---------------|--------|--------|--------|--------|--------|-------|
| AWS | ≤ 0.30 | ≤ 1.75 | ≤ 0.60 | ≤ 0.03 | ≤ 0.03 | ≤ 1.8 |
| EN ISO | - | ≤ 2.0 | - | - | - | ≤ 2.0 |
| Typical value | 0.25 | 0.45 | 0.30 | 0.012 | 0.004 | 1.40 |

Typical mechanical properties of weld metal:

| | Yield strength MPa(ksi) | Tensile strength MPa(ksi) | Elongation % |
|---------------|----------------------------|------------------------------|-----------------|
| AWS | ≥ 390(58) | 490-670(70-95) | ≥ 22 |
| EN ISO | ≥ 420(61) | 500-640(73-93) | ≥ 20 |
| Typical value | 430(62) | 600(87) | 25 |

Welding position:



Sizes and recommended parameter range (DC<+>) :

Stick out: 40-60 (mm)

| Position | Diameter (mm) | 2.4 | 2.8 |
|----------|---------------|-----|-------------------|
| | F, HF | | 250A-400A/26V-34V |

* The information contained or otherwise referenced herein is presented only as "typical" without guarantee or warranty, and TienTai Electrode Co., Ltd. expressly disclaims any liability incurred from any reliance thereon. Typical data is obtained when welded and tested in accordance with AWS specification. Other tests and procedures may produce different results. No data is to be construed as recommendation for any welding condition or technique not controlled by TienTai Electrode Co., Ltd.