

# TFW-308H

AWS A5.22 E308HT1-1  
JIS Z 3323 TS 308H-F C 1 1

## Characteristics and Applications:

TFW-308H is designed for 100% CO<sub>2</sub> gas and all-position welding. It exhibits excellent slag release. An 19Cr-9Ni austenitic stainless steel deposited can be used for joining 18Cr-8Ni austenitic steels such as AISI304. AISI301. 302. SUS304H. It provides good resistance to inter-granular corrosion and has higher tensile strength than TFW-308L. It also can be used as an intermediate layer for hardfacing.

## Notes on usage:

1. Before welding, oil, rusty, and moisture should be cleaned off the base material that should have the proper protection from the wind in welding site.
2. Use 99.8% purity or higher CO<sub>2</sub> shielding gas.
3. Keep the product dry, while it is stored or delivered.

## Typical chemical composition of weld metal (wt%):

	C	Mn	Si	P	S	Cr	Ni	Mo	Cu
AWS	0.04-0.08	0.5-2.5	≤ 1.0	≤ 0.04	≤ 0.03	18.0-21.0	9.0-11.0	≤ 0.75	≤ 0.75
Typical value	0.05	1.50	0.50	0.023	0.008	19.90	9.80	0.07	0.15

## Typical mechanical properties of weld metal:

	Tensile strength MPa(ksi)	Elongation %
AWS	≥ 550(80)	≥ 30
Typical value	586(85)	40

## Welding position:



## Sizes and recommended parameter range (DC <+>):

Stick out:15-20(mm),flow rate:20-25(l/min):

Position	Diameter (mm)	1.2
F		140-220A / 23~33V
H		140-220A / 23~33V
VU、OH		120-200A / 24~30V

\* The information contained or otherwise referenced herein is presented only as "typical" without guarantee or warranty, and TienTai Electrode Co., Ltd. expressly disclaims any liability incurred from any reliance thereon. Typical data is obtained when welded and tested in accordance with AWS specification. Other tests and procedures may produce different results. No data is to be construed as recommendation for any welding condition or technique not controlled by TienTai Electrode Co., Ltd.