

# TF-81

An agglomerated flux for SAW

## Characteristics and Applications:

TF-81 is a neutral agglomerated flux for SAW. During welding, it won't result any significant changes composition of weld bead and thus the arc length by changing arc voltage,. This makes TF-81 very suitable for using with wire for hardfacing applications such as TWH- 12-S, 17-S, 31-S, and TWS-410NiMo-S, 420-S, etc.

## Notes on usage:

- 1.Dry flux at 300~350°C for 1~2hr if you are concern about moisture pick-up while opening the pack.
- 2.Add reasonable amount of new flux when recycled flux is used.

\* The information contained or otherwise referenced herein is presented only as "typical" without guarantee or warranty, and TienTai Electrode Co., Ltd. expressly disclaims any liability incurred from any reliance thereon. Typical data is obtained when welded and tested in accordance with AWS specification. Other tests and procedures may produce different results. No data is to be construed as recommendation for any welding condition or technique not controlled by TienTai Electrode Co., Ltd.