

# TS-309LB

AWS A5.4 E309L-15  
EN ISO 3581-B ES309L-15  
JIS Z3221 ES309L-15

## Characteristics and Applications:

The weld metal of TS-309LB contains more Cr, Ni than TS-308LB. The microstructure containing suitable quantity of ferrite gives it an excellent resistance to hot cracking. The welding can be done in all positions with good X-ray soundness and good mechanical properties. The product produces good notch toughness at the temperature as low as -46°C. It is suitable for welding of dissimilar metals of mild steel and steel stainless, hardening alloy steel and steel with poor weldability.

## Notes on usage:

1. Dry the electrodes at 300-350°C for 60 minutes and keep at 100-150°C before using.
2. Use lower currents for dissimilar metals welding.

## Typical chemical composition of weld metal (wt%):

	C	Mn	Si	P	S	Cr	Ni
AWS	≤0.04	0.5-2.5	≤1.00	≤0.04	≤0.03	22.0-25.0	12.0-14.0
EN ISO	≤0.04	0.5-2.5	≤1.00	≤0.04	≤0.03	22.0-25.0	12.0-14.0
Typical value	0.04	1.23	0.27	0.020	0.012	22.7	13.2

## Typical mechanical properties of weld metal:

	Tensile strength MPa(ksi)	Elongation %	Charpy V-Notch J (ft-lbf) -46°C (-51°F)
AWS	≥520(75)	≥30	-
EN ISO	≥520(75)	≥25	-
Typical value	570(83)	40	55(41)

## Welding position:



## Sizes and recommended operating range (AC or DC <+>):

Diameter (mm)	2.6	3.2	4.0	4.8
Length (mm)	300	350	350	350
Current (Amps)	F	60-90	80-130	130-170
	V&OH	50-80	70-110	100-130
				160-210
				-

\* The information contained or otherwise referenced herein is presented only as "typical" without guarantee or warranty, and TienTai Electrode Co., Ltd. expressly disclaims any liability incurred from any reliance thereon. Typical data is obtained when welded and tested in accordance with AWS specification. Other tests and procedures may produce different results. No data is to be construed as recommendation for any welding condition or technique not controlled by TienTai Electrode Co., Ltd.