

TM-77

AWS A5.18 E70C-6M
EN ISO 17632-A-T 46 4 M M21 3 H5
JIS Z 3313 T 49 4 T15-0 M A-U

Characteristics and Applications:

TM-77 is a gas-shielded metal-cored wire that features smooth spray arc, slag-free welds, low spatter, low diffusible hydrogen low fume emission and excellent low temperature impact toughness down to -40°C. It welds with a wider penetration profile and higher deposition efficiency than solid wire.

Multi-layer welding can be performed without removing slag. It is suitable for steel structures, storage vessels and multi-layer welding on heavy plate thickness.

Notes on usage:

1. Use DC(+) polarity.
2. Ar-CO₂ mixture. 75%~80%Ar+25%~20%CO₂.
3. Inter-pass temperature should be under 150°C while in multiple-pass welding.
4. Keep the product dry, while it is stored or delivered.

Typical chemical composition of weld metal (wt%):

	C	Mn	Si	P	S
AWS	≤ 0.12	≤ 1.75	≤ 0.90	≤ 0.03	≤ 0.03
EN ISO	-	≤ 2.0	-	-	-
Typical value	0.04	1.45	0.54	0.010	0.008

Typical mechanical properties of weld metal:

	Yield strength MPa(ksi)	Tensile strength MPa(ksi)	Elongation %	Charpy V-Notch J (ft-lbf) -40°C(-40°F)
AWS	≥ 390(58)	490-670(70-95)	≥ 22	≥ 27(20)
EN ISO	≥ 460(67)	530-680(77-99)	≥ 20	≥ 47(35)
Typical value	560(81)	615(89)	26	65(48)

Welding position:



Sizes and recommended parameter range (DC < + >):

Stick out: 15-25 (mm) , flow rate: 20-25 (l/min)

Position	Diameter (mm)	1.2	1.4	1.6
	F, HF		240A-320A/26V-34V	260A-340A/27V-34V

* The information contained or otherwise referenced herein is presented only as "typical" without guarantee or warranty, and TienTai Electrode Co., Ltd. expressly disclaims any liability incurred from any reliance thereon. Typical data is obtained when welded and tested in accordance with AWS specification. Other tests and procedures may produce different results. No data is to be construed as recommendation for any welding condition or technique not controlled by TienTai Electrode Co., Ltd.