

TH-MN

AWS A5.13 EFeMn-A

Characteristics and Applications:

TH-MN deposits the weld metal of high 13Mn austenitic structure for repair welding. The weld metal provides good crack resistance due to the Ni (3%) content. Work hardening, tensile strength, toughness and mechanical properties are excellent and available for machining and cutting after welding.

Notes on usage:

1. Dry the electrodes at 150-200°C for 30-60 minutes before using.
2. When the base metal (13%Mn steel) is hardened, remove off the hardened zone before Welding. Low current without pre-heating are recommended during welding.
3. Clean up the contaminations on the base metal to avoid porosity and crack.
4. Use back-step method to prevent arc starting from blowholes and hold for 3-5 seconds at every end-up.
5. Maintain short arc length. Moving range should be controlled within 2.5 times of the wire's dia when you are welding with weave method.
6. Austenitic stainless stick electrode (ex TS-309/309L) is recommended for root pass of high-carbon steel and low-alloy steel.



Crusher Cone

Typical chemical composition of weld metal (wt%):

	C	Mn	Si	Ni
AWS	0.5-1.0	12-16	≤1.3	2.5-5.0
Typical value	0.60	14.5	0.13	3.2

Typical hardness of weld metal:

Testing Condition	Vicker's Hardness (HV)	Rockwell's Hardness (HRC)	Shore's Hardness (HS)
Interpass temp.130°C	80	-	-
Work Hardening	490	48	65

Welding position:



Sizes and recommended current range (AC or DC <+>):

Diameter (mm)	3.2	4.0	5.0
Length (mm)	350	350	450
Amps	90-140	140-190	190-240

* The information contained or otherwise referenced herein is presented only as "typical" without guarantee or warranty, and TienTai Electrode Co., Ltd. expressly disclaims any liability incurred from any reliance thereon. Typical data is obtained when welded and tested in accordance with AWS specification. Other tests and procedures may produce different results. No data is to be construed as recommendation for any welding condition or technique not controlled by TienTai Electrode Co., Ltd.