

TF-650

鹽基度: 1.8

相當規格：

EN ISO 14174 S A AB 1 67 AC H5

特性與用途：

為半鹼性燒結型鋸藥，適用於單及多電極(最多五電極)潛弧鋸接。在寬範圍的鋸接參數有良好的鋸接性及低消耗比率的鋸藥特性。由於具高速鋸接特性，特別適用於API 5L X70縱向鋸縫(UO)管件(兩面各一道或多層鋸接技術)製造的鋸接。鋸後鋸冠低而平順，在介面無鋸蝕(咬邊)現象，鋸道外觀及脫渣性，甚至在窄鋸縫鋸接均非常優異。具有低氫含量、低氧含量、低氮含量，有穩定的機械性質及低溫衝擊韌性。

注意事項：

- (1) 拆封後請置於爐中以 300~350°C 烘乾 2~4 小時再進行鋸接。
- (2) 鋸藥重複使用時，請加入適量的新鋸藥混合使用，可確保良好的鋸道品質。

鋸道化學成份之一例(wt%)：

搭配線材	EN ISO 14171-A	C	Si	Mn	P	S
TSW-12KM	S 38 2 AB S2Si	0.06	0.31	1.49	≤0.025	≤0.010
TSW-12KH	S 42 5 AB S3Si	0.07	0.34	1.74	≤0.025	≤0.010

鋸道機械性質之一例：

搭配線材	AWS A5.17	降伏強度 MPa(ksi)	抗拉強度 MPa(ksi)	伸長率 %	衝擊值 J (ft-lbf)	溫度 °C(°F)
TSW-12KM	F7A2-EM12K	443(64)	496(72)	37	40(30)	-30(-20)
TSW-12KH	F7A6-EH12K	459(67)	546(79)	38	80(59)	-51(-60)

* The information contained or otherwise referenced herein is presented only as "typical" without guarantee or warranty, and TienTai Electrode Co., Ltd. expressly disclaims any liability incurred from any reliance thereon. Typical data is obtained when welded and tested in accordance with AWS specification. Other tests and procedures may produce different results. No data is to be construed as recommendation for any welding condition or technique not controlled by TienTai Electrode Co., Ltd.



天泰鋸材
AN ILLINOIS TOOL WORKS COMPANY

台灣 · 台南市仁德區保安里開發四路六號
TEL:886-6-2663721 /FAX:886-6-2664301
E-mail:tworder@itwweld.com
http://www.tientai.com