

# TF-666

Basicity index: 1.3

EN ISO 14174 S AAB 1 68 AC H5

## Characteristics and Application:

TF-666 is an agglomerated submerged-arc welding flux, and it is specifically designed for fillet welding and, multi-pass butt welding of mild high tensile steels.

When using plates with heavy scales, TF-666 still provides smooth bead appearance and high porosity resistance. It also shows good operability both in single and multi-wire systems.

It is suitable for welding of steel structures (H-Beam, Box), pressure vessel and shipbuilding etc.

## Notes on usages :

1. Flux should be used immediately after taking out from can Damp. Flux should be re-dried at 300~350°C for 1~2hr holding time.
2. Adding proper quantity of new flux with the used one to maintain good quality of weld metal.

## Typical chemical composition of weld metal (wt %) :

Wire	EN ISO 14171-A	C	Si	Mn	P	S
TSW-12KM	S 42 3 AB S2Si	0.058	0.43	1.45	0.029	0.016
SubCor M13K	-	0.06	0.30	1.46	0.027	0.010

## Typical mechanical properties of weld metal:

Wire	AWS A5.17	Yield strength MPa(ksi)	Tensile strength MPa(ksi)	Elongation %	Charpy V-Notch J (ft-lbf)	Temperature °C(°F)
TSW-12KM	F7A2 -EM12K	454(66)	533(77)	33	60(44)	-30(-20)
SubCor M13K	F7A6-EC1	452(66)	525(76)	35	55(41)	-51(-60)

\* The information contained or otherwise referenced herein is presented only as "typical" without guarantee or warranty, and TienTai Electrode Co., Ltd. expressly disclaims any liability incurred from any reliance thereon. Typical data is obtained when welded and tested in accordance with AWS specification. Other tests and procedures may produce different results. No data is to be construed as recommendation for any welding condition or technique not controlled by TienTai Electrode Co., Ltd.