

TFS-300

Basicity index: 2.4

EN ISO 14174 S A FB 2 AC

Characteristics and Applications:

TFS-300 is a neutral bonded flux, which has good weldability, excellent slag removal and smooth bead appearance. Some alloys were suitably added to maintain the stability of the alloy content in weld metal. It features very sophisticated mechanical properties and corrosion resistibility.

- Stainless308, 308L, 316 and 316L butt join.
- Pressure vessel

Notes on usage:

1. Use low heat input to keep the corrosion resistibility and mechanical properties on heat-affected zone unchanged.
2. Bake at 300~350°C for 1-2hr before use.
3. Add reasonable new flux when recycle the used flux so as to maintain good welding quality.

Typical chemical composition of weld metal (wt %):

Wire	C	Mn	Si	P	S	Cr	Ni	Mo
TW-308L	0.04	1.50	0.46	0.020	0.015	19.5	10.7	-
TW-309L	0.04	1.57	0.47	0.023	0.005	22.5	12.5	-
TW-316L	0.04	1.73	0.50	0.025	0.008	18.0	11.5	2.45
TW-317L	0.035	1.43	0.45	0.025	0.013	18.5	13.6	3.38

Typical mechanical properties of weld metal:

Wire	AWS A5.39	Tensile strength MPa(ksi)	Elongation %	Charpy V-Notch J (ft-lbf)		
				-101°C (-150°F)	-110°C (-166°F)	-196°C (-320°F)
TW-308L	F75A32- ER308L/308L	570(83)	40	-	45(33)	40(30)
TW-309L	F75A4- ER309L/309L	545(79)	38	-	60(44)	35(26)
TW-316L	F75A32- ER316L/316L	550(80)	43	-	50(37)	40(30)
TW-317L	F75A15- ER317L/317L	578(84)	36	47(35)	-	-

* The information contained or otherwise referenced herein is presented only as "typical" without guarantee or warranty, and TienTai Electrode Co., Ltd. expressly disclaims any liability incurred from any reliance thereon. Typical data is obtained when welded and tested in accordance with AWS specification. Other tests and procedures may produce different results. No data is to be construed as recommendation for any welding condition or technique not controlled by TienTai Electrode Co., Ltd.