

SL-305

Basicity : 0.8

EN ISO 14174 SA CS 2B DC

Characteristics and Applications:

SL-305 is an agglomerate SAW strip cladding flux. It is suitable for 300 series stainless steel with good wet ability, smooth bead appearance & great slag detach ability. Due to SAW cladding, it could provide good merging between cladding layer & base metal. SL-305 could be applied in pressure vessel for stainless steel cladding.

Notes on usage:

1. Flux exposed to atmosphere for an excess period must be re-baked at 300-350°C for 1~2hr holding time.
2. Re-circulation of flux should be mixed with twice its volume of new flux prior to further use.
3. We recommend using heated hoppers for storage of flux in production.

Typical chemical composition of weld metal (wt%):

Deposit Type	Strip	Layer	C	Si	Mn	Mo	Cr	Ni	Cu	Nb
308L	TBD-309L	1st layer: Strip	0.02	0.38	1.63	0.05	23.31	13.03	0.036	--
	TBD-308L	2nd layer: Strip	0.01	0.34	1.63	0.02	20.33	10.25	0.029	--
		2nd layer: Weld metal	0.03	0.95	0.77	0.02	18.99	10.24	0.029	--
316L	TBD-309L	1st layer: Strip	0.02	0.38	1.63	0.05	23.31	13.03	0.036	--
	TBD-316L	2nd layer: Strip	0.02	0.31	1.75	2.57	18.67	12.81	0.021	--
		2nd layer: Weld metal	0.03	0.90	0.88	1.97	17.80	11.90	0.051	--
347	TBD-309L	1st layer: Strip	0.02	0.38	1.63	0.05	23.31	13.03	0.036	--
	TBD-347	2nd layer: Strip	0.01	0.38	1.78	0.07	19.73	10.26	0.048	0.47
		2nd layer: Weld metal	0.03	0.94	0.90	0.06	19.03	10.37	0.042	0.29

Remark:

1. Typical welding parameter : Strip :0.5X60mm, DC+/750A/28V/12cpm/ESO: 35mm/Flux Covered: 40mm Interpass temperature <150°C
2. The chemistry will be influenced by welding parameter 、welding equipment and bead thickness etc.

Size of strip:

Width & Thickness: 30 x 0,5mm, 60 x 0,5mm, 90 x 0,5mm

* The information contained or otherwise referenced herein is presented only as "typical" without guarantee or warranty, and TienTai Electrode Co., Ltd. expressly disclaims any liability incurred from any reliance thereon. Typical data is obtained when welded and tested in accordance with AWS specification. Other tests and procedures may produce different results. No data is to be construed as recommendation for any welding condition or technique not controlled by TienTai Electrode Co., Ltd.